

MONARCH INDUSTRIAL PRODUCTS (I) PVT. LTD.

Crusher Backing Compound
KrushMore
Heavy Duty Crushing Compound

CHEMICAL RESISTANCE CHART

Sl.No.	CHEMICALS	PERFORMANCE
1	Ammonia	Excellent
2	Cutting Oil	Excellent
3	Gasoline (Unleaded)	Fair
4	Hydrochloric 10%	very Good
5	Hydrochloric 36% F	Fair
6	Mineral Spirits	Excellent
7	Potassium Hydroxide 20%	Excellent
8	Potassium Hydroxide 40%	Excellent
9	Sodium Chloride Brine	Excellent
10	Xylene	Excellent

Chemical resistance is calculated with a 7 day, room temp. cure
(30 days immersion) @ 25°C

Note :